

Product	Glassfiber Sample Pad for Rapid Test
Intended Use	Development/Manufacture of Lateral Flow Immunoassay Test Kit
Product Variant	Type GFB-R* (GFB-R4, GFB-R7L)
Composition	Proprietary fibrous material

Physical Properties

Property	GFB-R* (0.35)	GFB-R* (0.6)
Appearance	White	White
Tare weight (mg/cm ²)	5.5±1.5	9±3
Thickness	370±70µm	610±120µm

Performance Characteristics

Product	Mean Wicking Time (Seconds) 4cm Distance with Distilled Water	
	GFB-R4	GFB-R7L
GFB-R*(0.35)	50±20	--
GFB-R*(0.6)	50±20	55±20

Supply Format Strip/sheet of desired dimension

Storage Condition Store and handle in accordance with all current regulations and standards.
Store in original foil packing at 1 - 35 °C. Avoid direct sunlight.

Caution: Material should be kept away from heat radiators.

Shelf Life Two Year from the date of dispatch, stored under above conditions.

Ordering Information

Product	Description			
Type	Thickness (mm)	Strip/Sheet Length	Strip/Sheet Width	Quantity (Nos.)
GFB-R4	0.35	As per requirement	As per requirement	As per requirement
GFB-R7L	0.6			

Example:

GFB-R4	0.35	300 mm	20 mm	-- Nos.
--------	------	--------	-------	---------

DSTGFBR1034E